



UPPERFLOK



VISCOSE
FLOK



160°C



PEEL : COLD



Flock Blade 60°
Medium Pressure



300 µm



15 - 20 Sec.

SPECIFICATIONS

APPLICATION

1. Cut the material in reverse with a Flok blade
2. Weed the excess material
3. Heat press on a SEFA machine on the garment at 160 ° C & Protect the polyester carrier with silicone paper 15 - 20 sec - medium pressure
4. Peel the carrier off when cold

THICKNESS:  Viscose Flok 300 µm

CARRIER: Adhesive & Transparent polyester



APPLIES ON

Cotton ● Polyester ● Acrylic & Similar Fibres

CARE & MAINTENANCE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only

WASH

- Max 90° C
- Preferably inside out
- Do not bleach
- Tumble-dry approved
- Dry-cleaning approved

STORE

- Up to 1 year
- In a dry room (15-30° C)
- Away from sunlight
- In vertical position


Heat transfers for textiles

NOTE: For best results, it is recommended to TEST prior to starting standard production